

BITUMINOUS EXTERIOR COATING

RECOMMENDED USES: FRESH AND SALT WATER DAMP PROOFING AND WATERPROOFING AND CHEMICAL EXPOSURES.

COLOR: BLACK

DESCRIPTION: A SELF PRIMING THIXOTROPIC, NON-SPECIFICATION GRADE COAL TAR PROTECTION COATING USED IN THE PROTECTION OF METAL AND MASONRY SURFACES. IDEAL FOR IMMERSION AND WASTE SERVICE.
CONFORMS TO SPECIFICATIONS: SOLIDS OF MATERIAL MEETS ASTM D450

PHYSICAL AND CHEMICAL PROPERTIES:

PERCENT SOLIDS, BY:

WEIGHT: 75+2%

VOLUME: 65+2%

FLASH POINT: 80° F (PENSKY MARTIN)

WEIGHT PER GALLON @ 77°F: 10.2-10.8

VOC PER GALLONS: 2.85 LBS. MAXIMUM

HEAT RESISTANCE: 155° F DRY, 115° F WET

RECOMMENDED FILM THICKNESS:

WET: 20-25 MILS PER COAT

DRY: 15-18 MILS PER COAT

COVERAGE PER GALLON: 60-80 SQ. FT. (ASSUMES NO LOSS OR SURFACE POROSITY)

SHELF LIFE: TWO YEARS

RECOMMENDED STORAGE CONDITIONS: FOR BEST APPLICATION RESULTS, MAINTAIN PRODUCT IN HEATED STORAGE (70° - 80° F) FOR AT LEAST 24 HOURS PRIOR TO APPLICATION.

RECOMMENDED THINNER: COOPER BLACK 750 OR XYLENE, IF NECESSARY

RECOMMENDED CLEANER: COOPER BLACK 750 OR XYLENE

RECOMMENDED APPLICATION TEMPERATURE RANGE: APPLY MATERIAL ONLY WHEN MATERIAL, SURFACE, AND AIR TEMPERATURE IS 50° F AND RISING. DRY TIME @ 77° F AND 50% RELATIVE HUMIDITY:

TACK FREE 24-36 HOURS

RECOAT 72 HOURS

FULL CURE 8-10 DAYS

AS MANUFACTURED BY
COOPERS CREEK CHEMICAL CORPORATION



**Continental
Concrete
Products, Inc.**

1 South Grosstown Rd.
Pottstown, PA 19464
Phone: (610) 327-3700
Fax: (610) 327-9488

COOPER BLACK NO. 760 HEAVY DUTY PROTECTIVE COATING

SIGNATURE OF APPROVAL

DATE

AR

DWG

STRUCTURE

2/08/16

760HDPC